



221320110536

检测报告



中国认可
国际互认
检测
TESTING
CNAS L9023



第 1 页 共 4 页

报告编号 : HYI20241516X32469

检测报告

样品名称: 玻璃绝缘子

产品规格: U70B/146 70KN

检验类别: 委托检验

委托单位: 上海纳太电力有限公司

厦门泓益检测有限公司

检测专用章

This report shall not be altered, increased or deleted. The results shown in this test report refer only to the sample(s) tested. Without written approval of Hongyi Testing, this test report shall not be copied except in full and published as advertisement Hongyi Physical & Chemical Lab.

厦门泓益检测有限公司

Xiamen Hongyi Testing Co., Ltd.

地址: 福建省厦门市同安区轻工食品工业区美禾路 99 号

ADDRESS: No. 99 Meihé Road, Light Industry Food Industrial Zone, Tongan District, Xiamen City, Fujian Province,



221320110536

检测报告



中国认可
国际互认
检测
TESTING
CNAS L9023



第 2 页 共 4 页

报告编号 : HYI20241516X32469

样品名称	: 玻璃绝缘子	型号规格	: U70B/146 70KN
委托单位	: 上海纳太电力有限公司		
委托单位地址	: 上海市金山区亭林镇兴工路225号1幢(亭林经济二区)		
商标	: SHRT	送样数量	: 10 片
生产厂家	: 上海纳太电力有限公司		
生产厂家地址	: 上海市金山区亭林镇兴工路225号1幢(亭林经济二区)		
检验类别	: 委托检验	测试日期	: 2024 年 09 月 08 日至 2024 年 09 月 28 日
出报告日期	: 2024 年 10 月 08 日		
检测依据	: GB/T 1001.1-2003《标称电压高于 1000V 的架空线路绝缘子 第一部分：交流系统用瓷或玻璃绝缘子元件定义、试验方法和判定准则》 GB1001.1-2021 玻璃绝缘子 技术条件 JB/T9681-1999 高压线路标准玻璃绝缘子 IEC60383.1 规定		
样品参数	: /		
样品特征及条件	: 样品完好		
测试结果	: 根据客户要求依据标准对送检样品进行了检测，具体检测项见后续页		
环境温度	: (25±5) °C	环境湿度	: (25±20) %
报告编制:		报告审核:	
报告签发:			

This report shall not be altered, increased or deleted. The results shown in this test report refer only to the sample(s) tested. Without written approval of Hongyi Testing, this test report shall not be copied except in full and published as advertisement Hongyi Physical & Chemical Lab.

厦门泓益检测有限公司

Xiamen Hongyi Testing Co., Ltd.

地址: 福建省厦门市同安区轻工食品工业区美禾路 99 号

ADDRESS: No. 99 Meihai Road, Light Industry Food Industrial Zone, Tongan District, Xiamen City, Fujian Province,



221320110536

检测报告



中国认可
国际互认
检测
TESTING
CNAS L9023



第 3 页 共 4 页

报告编号 : HYI20241516X32469

测试结果:

序号	检测项目	单位	检测指标	检测结果	判定
1	尺寸(结构高度)	mm	146.0	146.0	合格
2	尺寸(绝缘体最大外径)	mm	255	255	合格
3	尺寸(爬电距离)	mm	320	320	合格
4	外观	-	绝缘子颜色均匀、表面光滑，无空隙、裂痕、金属性无毛刺飞边等缺陷，镀锌层连续，且均匀光滑，附着良好不起皮剥落。	外观良好	合格
5	拉伸负荷试验	KN	≥35	70	合格
6	工频击穿耐受电压	KV	≥130	130	合格
7	无线电干扰对地试验 (10KV, 1Mhz) 下)	-	≤50μV	符合要求	合格
8	工频湿耐受电压	KV	≥40	40	合格
9	雷电冲击干耐受电压	KV	≥100KV	不击穿, 不闪落	合格
10	电晕熄灭电压	KV	≥14	帽: 22KV 脚: 18KV	合格

This report shall not be altered, increased or deleted. The results shown in this test report refer only to the sample(s) tested. Without written approval of Hongyi Testing, this test report shall not be copied except in full and published as advertisement Hongyi Physical & Chemical Lab.

厦门泓益检测有限公司

Xiamen Hongyi Testing Co., Ltd.

地址: 福建省厦门市同安区轻工食品工业区美禾路 99 号

ADDRESS: No. 99 Meihé Road, Light Industry Food Industrial Zone, Tongan District, Xiamen City, Fujian Province,



221320110536

检测报告



中国认可
国际互认
检测
TESTING
CNAS L9023



第 4 页 共 4 页

报告编号 : HYI20241516X32469

注意事项:

1. 报告无“检验报告章”或检验单位公章无效。
2. 未经本实验室书面同意，不得部分复制本报告。
3. 报告无主检、审核、批准人签字无效。
4. 报告涂改无效。
5. 对检测报告若有异议，应于收到报告之日起十五日内向检测单位提出，逾期不予受理。
6. 委托检测仅对来样负责。

地址：福建省厦门市同安区轻工食品工业区美禾路 99 号

Add: No.99MeiheRoad,LightIndustryFoodIndustrialZone,TonganDistrict,XiamenCity,FujianProvince,



This report shall not be altered, increased or deleted. The results shown in this test report refer only to the sample(s) tested. Without written approval of Hongyi Testing, this test report shall not be copied except in full and published as advertisement Hongyi Physical & Chemical Lab.

厦门泓益检测有限公司

Xiamen Hongyi Testing Co., Ltd.

地址：福建省厦门市同安区轻工食品工业区美禾路 99 号

ADDRESS: No. 99 Meihe Road, Light Industry Food Industrial Zone, Tongan District, Xiamen City, Fujian Province,